

# **Admitex** *HIGRO 200*

## **PLASTICIZING AND SEALING ADDITIVE**

### **CHARACTERISTICS**

HIGRO 200 is a plasticizing and sealing additive. Thanks to its features it allows reduction of water absorption by concrete and what follows increase of its watertightness and frost resistance. Additionally it is possible to receive tight structure of concrete, which reduces the phenomenon of capillary raising. It reduces the number of carbonate efflorescence and intensifies staining of colorful product. Using the HIGRO 200 additive has a significant impact on durability of concrete elements.

### **USAGE**

- a textural layer of sett
- curbs, edges
- pipes and concrete rings
- cracked, ground sett etc.

### **DOSAGE**

The scope of dosage from 0.3 % to 2 % of the cement mass. Recommended 0.4% - 0.8%.

The additive should be dosed to batch water during its dosage or directly to concrete mix. Stir the additive before use. The optimum dosage of the additive should be defined on the basis of sample tests.

Time of mixing should also be defined on the basis of performed tests. The time of additive activation should be less than 60 seconds.



# **Admitex** *HIGRO 200*

## **PLASTICIZING AND SEALING ADDITIVE**

### **TECHNICAL DATA**

Colour: milk

Density:  $1.0 \pm 0.02$  kg/dm<sup>3</sup>

pH : 8 - 9

The content of chlorides: < 0.10%

### **STORAGE**

Store in roofed rooms, in tightly closed packages in the temperature from 5 to 20°C. Stir after long storage. Protect from frost or overheat. Date of expiry 12 months.

### **PACKAGING AND TRANSPORT**

- in 1000-liter return containers,
- transport in locked means of transport, not subject to ADR limitations,

### **SAFETY PREAUTIONS**

HIGRO 200 is not a hazardous material. Handle in accordance with the assumed rules of safety. In case of getting dirty take off clothes and cleanse dirty skin with a large amount of water. Detail information regarding health, safety available in the Characteristics Sheet.



# ***Admitex*** **HIGRO 200**

## **PLASTICIZING AND SEALING ADDITIVE**

### **REMARKS**

Data included in Information Sheet is of approximate nature and was presented on the basis of experience in production and practical use. Due to various use of raw materials and individual features of production lines, one should perform adequate technological samples and tests.

The product guarantee comprises the material stored in original, tightly sealed packages, in conditions as described above.

In case of any further questions please contact us under the following telephone number: 32 601 24 79

