

Admitex MURA

ADDITIVE FOR MORTARS

CHARACTERISTICS

ADMITEK MURA is an additive intended for production of cement and sand mortars in a concrete batching plant or directly on the building site. Thanks to aerating components the mortar has very good workability and adhesiveness to surface as well as increased frost resistance features. The delaying substances enable extension of usage of the mortar even up to 72 hours.

USAGE

- Wide usage, everywhere where we use mortar,
- for all types of cements

DOSAGE

The additive should be added in the scope of 1.0-2.0% of binder mass and is dependent on the assumed technical requirements and on the type of cement and granulation of sand. Dose together with batch water. The time of mixing should be precisely defined.

TECHNICAL DATA

Base: aerating and delaying measures

Color: colorless

Density: 1.1 g/cm \pm 0.02

Content of chlorides < 0.1%



STORAGE

Store in roofed rooms, in tightly closed packages in the temperature from 5 to 40C. Stir after long storage or freezing. The product is non-flammable. The date of expiry is 12 months.

PACKAGING AND TRANSPORT

- in 1000-liter return containers,
- in 200-liter return plastic barrels,
- transport in locked means of transport, not subject to ADR limitations,
- the additive is practically a non-hazardous product,

SAFETY PRECAUTIONS

ADMITEK MURA is not a hazardous material. Handle in accordance with the assumed rules of safety. Avoid contact with eyes, mucosa and skin. In case of getting dirty take off clothes and cleanse dirty skin with a large amount of water. Detail information regarding health, safety is available in the Characteristics Sheet.

REMARKS

Data included in Information Sheet is of approximate nature and was presented on the basis of experience in production and practical use. Due to different use of raw materials by production of concrete one should perform appropriate tests and examinations. The guarantee of quality comprises only sale and delivery of the product and does not comprise the method of product storage by the client.

In case of any further questions please contact us under the following telephone number: **32 601 24 79**

